

01 31

Magnesite Sand (Colen Clay)

MgO = 83% Min.

SiO₂ = 5% Max.

CaO = 6% Max.

Loss on ignition at 1600°C = 1.5% Max.

Size: Less than 2 mm = 40% Max.

2 - 8 mm = 60% Min.

Powder through 140 mesh = 15% Max.

CIF


SF


DMC (PPC - 17)
PPC